

# ALL-STAR



- All-Star is a premium quality rotary joint compound containing 60% finely powdered metallic lead to absorb shock and protect connections from thread galling and seizing under balanced high loads. Non-metallic particles is used in the formulation to prevent metal compaction in the shoulder and thread roots ensuring a clean breakout.

## ■ Product Specifications

Service Rating	200°C / 392° F
Drop Point	240°C / 464° F
Brushability	-18°C / 0° F
Torque Correction Factor	1.11

NOTE: The torque correction factor is influenced by a variety of conditions such as pipe size, thread geometry, drilling mud contaminants, and drilling environment. In all applications experience and prior knowledge should be used to adjust make-up torques as the torque correction number provided is relative.

## ■ Service Recommendations

Drill collars at maximum torque in severe drilling conditions

## ■ Packaging

10 L Metal /2.5 gal	Net 20.4 kg	Net 45 lb
---------------------	-------------	-----------

Refer to Manufacturer's Material Safety Data Sheet for Precautionary and Handling Information

